




Imaging

Images do not accurately portray size or color.

Accu-Vu™ Imaging:



Comments:

Document No: 1119996 Validation Date: 21 January 2022

Identification

Mineral Type: Natural Beryl Transparency: Transparent

Variety: Emerald Color Description: Green

Carat Weight: 6.00 cts Shape: Rectangular

Measurements: 11.37 x 10.62 x 7.80 mm Cutting Style: Emerald Cut

Comments:

Identification

American Gemological Laboratories™
America's first and most highly respected origin lab.

Founded in 1977,
AGL is an internationally recognized gemstone
testing facility, specializing in comprehensive
colored stone analyses.

AGL has the distinction of being the
first laboratory in the United States to issue
Country-of-Origin reports. Our company and its
principals have a long tradition of research into the
detection of and reporting on gem identification-
and-classification, gemstone treatments and
provenance determinations.

Our staff is composed of experts in the field
of gemstone testing and reporting. Our findings
reflect the latest knowledge and analytical
techniques to ensure the highest standards
are applied on every stone we test.

AGL's testing and reporting
methodology provide you with unsurpassed quality
and reliability. We are committed to providing
the highest level of service and reporting
that our clients and the industry have
come to expect from the AGL.

Origin

Origin
Provenance: Colombia

Comments: Based on available gemological information, it is the opinion of the
Laboratory that the origin of this material would be classified as
Colombia.



Enhancement

Standard: Clarity Additional: None

Degree: Minor

Type: Oil-type

Stability Index: Very Good to Good

Comments: Emeralds are commonly clarity enhanced to reduce the visibility of fissures.
Oil is a traditional type of filling material used to reduce the visibility of fissures.

Enhancement

| | | | | | | | | | | | | | | | |
|-----------|-----------|------|------|------|----------------|-----------|------|----------|--------|-------------|---------------|-------|----------|--------|-----------|
| 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | 9 | 10 | None | Insignificant | Minor | Moderate | Strong | Prominent |
| Excellent | Very Good | Good | Fair | Poor | Extremely Rare | Very Rare | Rare | Uncommon | Common | Very Common | | | | | |

Enhancement Stability Index™

Degree of Clarity Enhancement & Relative Rarity™

General Report Comments:

M. Chaipaksa
Monrudee Chaipaksa, Senior Gemologist

Christopher P. Smith
Christopher P. Smith, President

