


Imaging

Images do not accurately portray size or color.

Accu-Vu™ Imaging:



Comments:

General Report Comments:

Document No: 1135802 A and B

Validation Date: 24 January 2024

Identification

Mineral Type: Natural Beryl  
Variety: Emerald

Transparency: Transparent  
Color Description: Green

Carat Weight: 5.29 and 4.68 cts  
Measurements: 17.51 x 8.33 x 6.12 mm  
and 17.38 x 8.10 x 5.49 mm

Shape: Pear  
Cutting Style: Modified Brilliant Cut

Comments: Two gemstones with a total weight of 9.97 cts.

Identification

American Gemological Laboratories™

America's first and most highly respected origin lab.

Founded in 1977,

AGL is an internationally recognized gemstone  
testing facility, specializing in comprehensive  
colored stone analyses.

AGL has the distinction of being the

first laboratory in the United States to issue

Country-of-Origin reports. Our company and its  
principals have a long tradition of research into the  
detection of and reporting on gem identification-  
and-classification, gemstone treatments and  
provenance determinations.

Our staff is composed of experts in the field  
of gemstone testing and reporting. Our findings  
reflect the latest knowledge and analytical  
techniques to ensure the highest standards  
are applied on every stone we test.

AGL's testing and reporting  
methodology provide you with unsurpassed quality  
and reliability. We are committed to providing  
the highest level of service and reporting  
that our clients and the industry have  
come to expect from the AGL.

About Us

Origin

Provenance: Colombia

Comments: Based on available gemological information, it is the opinion of the  
Laboratory that the origin of this material would be classified as  
Colombia.



Origin

Enhancement

Standard: Clarity  
Degree: Minor  
Type: Oil-type  
Stability Index: Very Good to Good

Additional: None

Comments: Emeralds are commonly clarity enhanced to reduce the visibility of fissures.  
Oil is a traditional type of filling material used to reduce the visibility of fissures.

Enhancement

1	2	3	4	5	6	7	8	9	10
Excellent	Very Good	Good	Fair	Poor					

Enhancement Stability Index™

None	Insignificant	Minor	Moderate	Strong	Prominent
Extremely Rare	Very Rare	Rare	Uncommon	Common	Very Common

Degree of Clarity Enhancement &amp; Relative Rarity™

*M. Chaipaksa*  
Monrudee Chaipaksa, Senior Gemologist

*Christopher P. Smith*  
Christopher P. Smith, President

